

ROUP OF COMPANY

R/O- Plot No. 120,A Block First Floor, Qutub Vihar Phase-1, Near Sec-19, Dwarka, New Delhi-110071 M- +91 9871417131, +91 8376920360 , E-admin@adhesivesolutions.in , Web- www.adhesivesolutions.in

3M VHB[™] Tapes

3M[™] VHB[™] Tapes Product Information

July 2013

| Product Description | 3M [™] VHB [™] Tapes are a family of double-sided foam tapes made from high performance acrylic adhesives. These tapes are able to form bonds of exceptional strength and have greater durability and elasticity than conventional double-sided foam tapes. The VHB Tape product range includes tapes with different core constructions and a variety of adhesives. All 3M VHB Tapes use closed cell technology, and provide outstanding environmental resistance and durability. The superior performance of 3M VHB Tapes means they can often be used to replace mechanical fasteners for joining a wide range of materials. |
|-------------------------------------|---|
| How 3M VHB Tapes Work | The exceptional performance of these tapes comes from the properties of the acrylic core. The core has the dual properties of behaving like a very viscous liquid and an elastic solid. This property is known as viscoelasticity. The "visco" properties allow the adhesive to flow into the microscopic irregularities of the surface to form very strong bonds. The elastic properties allow these tapes to absorb dynamic loads, accommodate differential expansion between surfaces and help distribute loads over the greatest possible area. The elastic properties are maintained between -40°C and 90°C. |
| The Benefits of Using VHB Tapes | No holes to drill, no riveting, no liquid adhesives to cure, no weld distortion, no clean up. Prevents corrosion by separating dissimilar metals. Is invisible and eliminates unsightly rivets, spot welds, screw-heads or nuts and bolts. Meets a wide range of holding requirements for tough applications involving glass, metals, woods, composites and many plastics. Damps vibration and reduces noise. Resists solvents and salt water. Seals and bonds even in extreme environments. Can compensate for thermal expansion and contraction of bonded parts. Distributes stress. Excellent for thin materials. Fast, clean and simple to apply. Reduces assembly costs. |
| Durability | Acrylic is a very durable chemistry with excellent long term aging resistance. 3M VHB Tape has been used in many long term and demanding applications in varied industries such as construction, signage and transportation. There are examples of successful applications of VHB Tapes dating back to 1980. Locally, VHB Tape was used in 1987 on the exterior cladding panels of the 227 building in Newmarket, Auckland. Durability is dependent on specific application and working conditions, and further detailed information is available in the <i>3M VHB Tape Durability Technical Bulletin</i> . |
| Outdoor Weathering | The performance of VHB Tapes is not significantly affected by exposure to sunlight and harsh environments. Outdoor weathering decks in Florida (hot and moist, high UV), and Arizona (hot |
| | with high UV) and other locations around the world are used to collect data on the long term performance of these tapes. These harsh tests typically show 100% bond strength retention after 2-5 years. |
| Fatigue and Vibration Resistance | with high UV) and other locations around the world are used to collect data on the long term performance of these tapes. These harsh tests typically show 100% bond strength retention after 2-5 years. An example of VHB Tape durability has been generated on the Bendix Automotive Proving Ground in Indiana, USA. A full size semi-truck with a sleeper cab was constructed with all exterior panels and doors taped to an underlying frame with 4950 VHB Tape. After approximately 500,000km on the harsh durability track the VHB Tape bonds remained completely intact. This is particularly impressive as some of the mechanically joined and welded parts failed and required repairs during the test program. |



| зій йнь тарег | roduct Selection |
|--|---|
| Step 1: Special Feature or General Purpose Product? | Special Feature products have special performance characteristics. Products are available for: Situations where high dynamic stresses are involved Applications to paints and plastics including plasticized vinyl Situations that require a transparent tape When the tape is applied between 0°C and 10°C Components that are bonded before powder coating or need to withstand higher temperatures General Purpose products are ideal for many interior and exterior industrial applications. These tapes have softer cores and are especially suited for textured surfaces or where sealing is required. The table on the next page describes the properties of the available VHB Tapes. |
| Step 2: What are the surfaces to be bonded? | All VHB Tapes provide good adhesion to most metals, glass and high surface energy plastics.* For higher performance on paints and plastics** use 4941, 4991, 5925, 5952, 5962 or 4945. The liner side of 4618, 4622 and 4624 has good adhesion to paints and plastics. Use General Purpose VHB Tapes or 4941 or 4991 when the surface is textured to get a more complete bond or when sealing the joint is a critical requirement. On flexible vinyls use only plasticizer resistant 4941, 4945 or 4991 (Note: the liner side of 4618, 4622 and 4624 is also plasticizer resistant). |
| | * High surface energy plastics include acrylic , ABS, polycarbonate , PVC, polyester, Polyamide, Polyimide, Phenolic, Noryl. ** Low surface energy plastics include PVA, EVA, polystyrene, acetal and some paints. They may require priming with 3M Tape Primer 94. Very low surface energy plastics such as polypropylene, polyethylene and EPDM are difficult surfaces to stick to. Primer 94 may improve the performance on these surfaces. See also the Surface Preparation Suggestions on the back page |
| Step 3: How thick does the tape have to be? | • The tape thickness required depends on the mismatch between the surfaces to be joined. The more closely the two surfaces fit together the thinner the tape can be. As a general rule the tape can accommodate up to 50% of its thickness in mismatch (i.e. the tape should be at least twice as thick as the mismatch). If in doubt, use a thicker tape to ensure a significant area of the tape forms a bond. |
| | When bonding sheets or large pieces, the thickness of the material should not be more than twice the tape thickness, e.g 1.1mm thick tape is commonly used to bond sheets up to 2.2mm thick. Thermal expansion and contraction or movement in the joint should not exceed three times the tape thickness. As a general rule, a 2.4m length of plastic can be bonded to metal using a 1.1mm thick tape. |
| Step 4: How much tape to use? | In shear (e.g. holding a sign or panel to a wall) the suggested amount of tape to hold up 1 kg Standard Tape Widths Tape Length 12.7 mm wide 430 mm 19.0 mm wide 290 mm 25.4 mm wide 215 mm These amounts of tape include a significant factor of safety to allow for the different properties of the tapes in the VHB Tape range. These amounts can be reduced by up to 50% depending on the tape type, if customer evaluation gives satisfactory results. |
| Step 5: What is the application temperature? | The desirable tape <u>application</u> temperature range is 20°C - 40°C. There are VHB Tapes with special properties that allow low temperature application . The minimum suggested surface temperatures for tape application are: 16°C: 4936, 4941, 4945, 4991 10°C: 4611, 4618, 4622, 4624, 4905, 4910, 4915, 4918, 4930, 4950, 4959, 5925, 5952, 5962, 9473 0°C: 4951, 4957 (on high surface energy substrates only) |

3M[™] VHB[™] Tapes Product Range

| | | Adhesive type | Product | Таре | Colour | Temperature Resistance | | Relative | Adhesion | | Application Ideas | |
|----------------------|-------------------------------------|--|---------|-----------|---------------------------------|---------------------------|---------------|-----------------|-----------------|--|---|-----|
| | | | Number | Thickness | | Minutes Hours | Days Weeks | HSE Material | LSE Material | Liner Type | | |
| | se | Modified adhesive on | 5925 | 0.64mm | Black adhesive, grey core | 149 °C | 121°C | High | Medium | Red Film | Excellent adhesion to the | |
| ral Purpo B Tapes | | both sides of a soft foam | 5952 | 1.1mm | adhesive, grey core Black | 149 °C | 121°C | High | Medium | Red Film | widest variety of surfaces, including most powder coated paints and plastics. | |
| | | | 5962 | 1.55mm | adhesive, grey core | 149 °C | 121°C | High | Medium | Red Film | | |
| | б 千 | Firm adhesive on one | 4618 | 0.64mm | White | 121°C | 93°C | High | Low | Green Film | | |
| | - Ger | side and a soft adhesive on the other | | 1.1mm | White | 121°C | 93°C | High | Low | Green Film | Good adhesion to a wide range of surfaces. | |
| | • | side of a medium foam | 4624 | 1.55mm | White | 121°C | 93°C | High | Low | Green Film | | |
| _ | | | 4930 | 0.64mm | White | 149°C | 93°C | High | Low | Paper | Lise with metals where high | |
| | | Firm adhesive on both | 4950 | 1.1mm | White | 149°C | 93°C | High | Low | Paper | dynamic stresses are | Ĺ |
| | | | 4959 | 3.0mm | White | 204°C | 149°C | High | Low | Clear Film | involved. | |
| | sec | Soft adhesive on both sides of a firm foam | 4945 | 1.1mm | White | 149°C | 93°C | High | Low | Paper | Use with metals and HSE plastics where high dynam stresses are involved. | |
| | a | Soft adhesive on both | 4936 | 0.64mm | Grey | 149°C | 93°C | High | Medium | Paper | Excellent adhesion to a | - |
| | | sides of a medium | 4941 | 1.1mm | Grey | 149°C | 93°C | High | Medium | Paper | wide range of materials | |
| | ШТ | foam | 4991 | 2.3mm | Grey | 121°C | 93°C | High | Medium | Red Film | including plasticised vinyl. | |
| | 5 | | 4905 | 0.5mm | Clear | 149°C | 93°C | Hiah | Low | Red Film | | _ |
| | e | . | 4910 | 1.0mm | Clear | 149°C | 93°C | High | Low | Red Film | For high surface energy | |
| | Ē | Clear firm adhesive | 4915 | 1.5mm | Clear | 149°C | 93°C | High | Low | Red Film | materials where a clear adhesive is required | i - |
| | a i | | 4918 | 2.0mm | Clear | 149°C | 93°C | High | Low | Red Film | adiresive is required. | |
| | ШЩ | Low temperature | 4951 | 1.1mm | White | 149°C | 93°C | High | Low | Clear Film | For HSE substrates where | |
| | <u></u> | of a firm foam | 4957 | 1.55mm | Grey | 149°C | 93°C | High | Low | Clear Film | temperatures down to 0 °C | ŀ |
| Spe | High temperature firm foam adhesive | 4611 | 1.1mm | Dark grey | 232°C | 149°C | High | Low | Red Film | High temperature resistance. Can be used or metals prior to powder coating. | | |
| | | High temperature firm adhesive transfer tape | 9473 | 0.25mm | Clear | 260°C | 149°C | High | Low | Paper | High temperature resistance. Thin laminating adhesive. | |

3M[™]VHB[™]Tapes Product Performance Guide

General Purpose VHB Tapes

| Tape # | | 4618 | 4622 | 4624 | 5925 | 5952 | 5962 |
|----------------|---------|------|------|------|------|------|------|
| Peel Adhesion | N/100mm | 300 | 350 | 350 | 300 | 350 | 350 |
| Normal Tensile | kPa | 580 | 480 | 380 | 620 | 620 | 620 |
| Dynamic Shear | kPa | 550 | 445 | 410 | 620 | 550 | 550 |
| Static Shear | g 22°C | 1000 | 1000 | 1000 | 1000 | 1000 | 1000 |
| | 66°C | 250 | 250 | 250 | 500 | 500 | 500 |
| | 93°C | 250 | 250 | 250 | 500 | 500 | 500 |
| | 121ºC | | | | 250 | 250 | 250 |

Special Feature VHB Tapes

| | | | | | | | | | | | | | | | | 1 |
|----------------|---------|------|------|------|------|------|------|------|------|------|------|------|------|------|-----|-----|
| Tape # | | 4611 | 4905 | 4910 | 4915 | 4918 | 4930 | 4941 | 4945 | 4950 | 4951 | 4957 | 4959 | 4991 | 947 | 3 |
| Peel Adhesion | N/100mm | 315 | 210 | 260 | 260 | 260 | 350 | 350 | 440 | 440 | 315 | 350 | 350 | 350 | 16 | D |
| Normal Tensile | kPa | 590 | 690 | 690 | 690 | 690 | 1100 | 585 | 970 | 970 | 760 | 515 | 520 | 480 | 69 | С |
| Dynamic Shear | kPa | 445 | 480 | 480 | | | 690 | 480 | 550 | 550 | 550 | 480 | 380 | 450 | 55 | С |
| Static Shear | g 22°C | 1500 | 1000 | 1000 | 1000 | 1000 | 1500 | 1000 | 1500 | 1500 | 1250 | 1000 | 1500 | 1000 | 100 | 0 |
| | 66°C | 750 | 500 | 500 | 500 | 500 | 500 | 500 | 500 | 1000 | 500 | 500 | 1000 | 500 | 100 | 0 |
| | 93°C | 750 | 500 | 500 | 500 | 500 | 500 | 500 | 500 | 500 | 500 | 500 | 750 | 500 | 100 | D |
| | 121ºC | 750 | | | | | | | | | | | 750 | | 100 | D |
| | 149°C | 750 | | | | | | | | | | | 750 | | 100 | D |
| | 177ºC | 750 | | | | | | | | | | | 750 | | | |
| | | • | | | | | | • | • | • | | • | | | | í – |



3M[™] VHB[™] Tapes Product Application

Introduction

Refer to the **Surface Preparation Suggestions** below, or to the *Surface Preparation for 3M VHB Tape Applications Technical Bulletin.*

- Most substrates common to VHB Tape applications are best prepared by wiping (in one direction) with a 50:50 mixture of isopropyl alcohol (IPA) and water.
- Where heavy oils or greases are present there may be a need to first cut the oil with a "degreasing" solvent, e.g. 3M Citrus Cleaner or white spirits, but this should always be followed with IPA/water cleaning to remove any residue.
- Abrasion or scuffing* of the surface will in many instances enhance adhesion by increasing the surface area available for bonding. Scuffing must be followed by cleaning with IPA/water mixture.
- The surface must be dry.
 A good way to assess cleanliness is that a surface prepared for VHB Tape application should be as clean as one being prepared for painting.

Making the Bond

Apply the tape to one surface leaving the liner in place. Apply pressure using a Scotch[™] brand PA-1 applicator or a roller. This ensures contact and removes air bubbles. Remove the liner, fit the two surfaces together carefully, and using a suitable roller apply

sufficient pressure to ensure the tape experiences 1 kg/cm² (100 kPa) pressure.



Step A: Some surfaces may need to be abraded using a 3M[™] Scotch-Brite[™] Abrasive Pad prior to cleaning.



Step E: Squeegee onto surface.



Step B: Solvent Wipe Note: Be sure to carefully read and follow solvent manufacturer's directions for use and precautions.



Step F: Remove liner.



Step C: Wipe dry.



Step D: Position tape. Handle tape by edges only.



Step H: Roll finished joint firmly.

Time/TemperatureBond strengths at the minimum application temperature will be achieved as follows:20 minutes50%24 hours90%1 hour75%3 days100%

be bonded.

Assemblies can be handled within 10 minutes but bonds should not be stressed before 72 hours

Step G: Position materials to

Surface Preparation Suggestions for Specific Materials

| Surface | Surface Preparation Suggestions | | | | | |
|--|---|--|--|--|--|--|
| Metals | Scuff if oxidized. For copper or brass apply lacquer or varnish to prevent further oxidation | | | | | |
| Aluminium, anodized | Clean only | | | | | |
| Some plastics & paints | Scuff, particularly on paints and hard plastics | | | | | |
| Plasticised vinyl | Evaluate plasticizer resistant tapes or prime with VHB Tape Primer 9639 | | | | | |
| Wood, concrete, brick | Seal surface with paint, varnish or thin coat of neoprene contact adhesive | | | | | |
| Glass/ceramic surfaces | Use Silane Glass Treatment AP115 in high moisture or humidity environments | | | | | |
| Low surface energy plastics | Prime with Primer 94 and evaluate suitability of VHB tape | | | | | |
| High Surface energy plastics with mould release | Clean with MEK or acetone (ensure solvents do not affect the plastic), then scuff, IPA/water wipe | | | | | |
| Fibreglass: Gelcoat | Clean with 3M General Purpose Adhesive Cleaner to remove mould release, scuff | | | | | |
| Non Gelcoat | Sand smooth, prime with thin coat of neoprene contact adhesive or gelcoat | | | | | |
| *Scuffing By hand: | Use Scotch-Brite [™] 7447 Hand Pads | | | | | |
| By Machine (Grinder): | Use Scotch-Brite [™] Roloc [™] Surface Conditioning Discs, medium or fine | | | | | |

3M New Zealand Ltd Industrial Adhesives and Tapes Division PO Box 33-246 Takapuna, Auckland Ph 0800 474787, Fax 0800 508980 E-mail: <u>3mnzib1@mmm.com</u> www.3m.com/vhb